

# **AQUAPRO 8069 Hitek Water Based Floor Finish**

AQUAPRO 8069 is a single pack, water based floor finish that exhibits excellent abrasion and chemical resistance.

### **Product Advantages**

- Easy to apply
- Excellent abrasion resistance
- Excellent chemical resistance, particularly when mixed with AQUAPRO 8720 Crosslinker
- Fast drying
- · Available in matt, satin and full gloss

## **Typical Applications**

Interior use only. Timber, particleboard or cork flooring.

Not suitable for exterior or wet area applications e.g. bathrooms or around swimming pools. Caution: floor will be slippery when wet.

# Product Properties Typical Properties

Build: Medium Colour: Clear

Sandability: Very Good Gloss: Matt, Satin & Full Gloss

Solvent Resistance: Excellent (with crosslinker)

Water Resistance: Very Good Levelling & Flow: Excellent

### **Product Approvals**

AQUAPRO 8069 has been evaluated for AS/NZS 4586:2004: Slip resistance classification of new pedestrian surface materials by Advanced Technology Testing & Research (ATTAR). The coating system passed the requirements of the "Dry Slip Resistance" and was classified as Dry = F. Certificates available on request.

When mixed with AQUAPRO 8930 Sure Grip Additive, AQUAPRO 8069 meets the standard AS/NZS 4586:2004 **Slip resistance classification of new pedestrian surface materials** – Appendix D (Oil-Wet Ramp Slip Resistance). **Classification group = R10**. Certificates available on request.

AQUAPRO 8069 complies with the Green Building Council Australia: Green Star – Office Design v3 & Office As Built v3, Table IEQ-13.1: Maximum TVOC Content Limits for Paints, Varnishes and Protective Coatings (Maximum limit for "One and two pack performance coatings for floors "EU Directive" – 140 g/L).

Coverage: 12-15 m² per litre

Coverage is dependent upon the porosity of the substrate.

Thinning: Not normally required

5-10% AQUAPRO 1300 Wet Edge Extender may be added in particularly hot environments where a high ambient room or floor temperature can be expected. Stir whilst adding.

AQUAPRO 8069 Issued 16 January 2018 Page 1

The information in this data sheet represents typical values. Application variables affect product performance therefore this information should be used as a guide. The user must satisfy themselves as to the suitability of this product for their requirements. Mirotone assumes no liability for use of this information.

#### **AQUAPRO 8720 Crosslinker:**

Adding AQUAPRO 8720 Crosslinker will improve chemical resistance and provide early abrasion resistance. This is ideal for commercial floors e.g. dance floors, restaurants, hotel foyers and receptions where limited time is available between coating the floor and resumption of usual floor use.

Add 20 mls of AQUAPRO 8720 Crosslinker per 1 litre of AQUAPRO 8069 Hitek e.g. 100mls in a 5L container of AQUAPRO 8069 Hitek.

# **Application Methods:**

Equipment: 6mm or 10mm nap roller cover or waterbased applicator and a high quality brush Preparing the floor to a professional standard is essential to achieve the best results.

- Fill all nail holes with a water based putty, allow to dry.
- Sand uncoated floor with 120-150 grade sandpaper or screenback on a flexible pad to ensure floor is uniformly dull with no sanding scratches, nibs or fur. Vacuum thoroughly. Take care to avoid scratching the surface.
- Apply a liberal first coat of AQUAPRO 8020 or 8069 or FASTASEAL 3528 or 3535 using a 6mm or 10mm nap
  roller cover and good quality brush to cut in around skirting boards and edges. Allow to dry per datasheet. To
  reduce the risk of tannin bleed, use FASTASEAL 3535.
- Thoroughly sand floor with 150-180 grade sandpaper or screenback, remove all nibs, fluff and fur. Vacuum all dust. Take care to avoid scratching the surface.
- Apply a coat of AQUAPRO 8069 Hitek. Allow to for 1 to 2 hours.
- Sand floor with 150-180 grade sandpaper or screenback. Vacuum all dust.
- Apply the final coat of AQUAPRO 8069 Hitek.

Note: AQUAPRO 8069 dries quickly, therefore it is important not to brush areas too far ahead of the roller or applicator bar at skirtings or edges so that a wet edge is maintained at all times, this will avoid a noticeable darker line in the finished floor around skirtings and floor edges. Uneven application may cause different wetting of the timber and consequently a different colour in higher build areas. Do not apply when temperature is less than 10°C or greater than 35°C.

Only pour sufficient coating to complete the job, replace the lid immediately as exposure to the environment can cause the product quality and performance to be affected. Do not return unused product to the can as this will cause the remaining material to increase in viscosity.

**Drying:** Recoat: 1-2 hours

Low temperatures and heavy film thickness will retard drying times. Direct sunlight and draft during drying may affect the final gloss level of the coating.

**Recommended Sealers:** AQUAPRO 8020 or 8069 (as its own sealer)

FASTASEAL 3528 or 3535

Application Equipment Clean Up: Clean all equipment using water.

Shelf Life: 12 months, see label for use by date.

Packaging: 5 litres

AQUAPRO 8069 Issued 16 January 2018 Page 2

#### Refer to the AQUAPRO Product Information Guide for more information.

Note: All coatings provide protection for the timber or substrate. However no coating is indestructible and all coatings will mark or scratch depending upon what comes into contact with the coating. Sharp objects including sand and grit will scratch the surface of any coated floor regardless of coating type. In high traffic commercial environments such as hair dressing salons, night clubs and taverns many factors need to be considered when choosing a coating system. Refer to the Product Information Guides for further information.

# **Health & Safety**

Before handling, refer to the Material Safety Data Sheet for health and safety information. Ensure that all personnel using this product have read and understood this data sheet and the associated MSDS and packaging label before using this product.

Note: Coatings give off strong solvents and odours during the drying process. People and pets should be removed from the building during the application and drying of coatings. All food and fabrics should also be removed to reduce the risk of them becoming tainted during the drying process.

Mirotone Pty Ltd Australia (Head Office)

ABN 40 000 041 136 21 Marigold Street, Revesby NSW 2212 Australia P +61 2 9795 3700 F +61 2 9771 3601 sales@mirotone.com.au Mirotone (NZ) Ltd New Zealand (Head Office)

32 Cryers Road, East Tamaki Auckland 2013, New Zealand P 0800 34 64 74 F 0800 34 64 34 information@mirotone.co.nz Mirotone (Thailand) Co., Ltd

83 Moo 4, Poochaosamingprai Rd, Samrong Klang, Prapradaeng, Samutprakam, 10130, Thailand P +66 2 754 4451 F +66 2 754 4450

www.mirotone.com

AQUAPRO 8069 Issued 16 January 2018 Page 3

The information in this data sheet represents typical values. Application variables affect product performance therefore this information should be used as a guide. The user must satisfy themselves as to the suitability of this product for their requirements. Mirotone assumes no liability for use of this information.